

Thomson PURE-PAC II

FDA compliant expanded PTFE compression packing ideal for colour sensitive applications. Full chemical range 0–14 pH.



FEATURES / BENEFITS

- Chemically inert (with a few exceptions over the entire 0–14 pH range).
- White, non-staining - for colour-sensitive applications.
- Thermally conductive - hybrid ePTFE yarn reduces shaft/sleeve wear: low coefficient of friction.
- FDA Compliant.
- High strength - extends service life.
- Resistant to aging and glazing.
- Excellent volume retention.

TYPICAL APPLICATIONS

- Pulp and Paper.
- Food and Beverage.
- Pharmaceutical.
- Colour-sensitive applications.
- Rotating equipment (mixers/agitators), centrifugal pumps, blenders, reactors, and valves.
- Slurries, powders, mild to medium abrasives.
- Aggressive Chemical service.

SPECIFICATIONS

Construction:

Expanded PTFE with proprietary FDA-compliant additives. Square interbraid.

Temperatures:

Min: -170°F (-112°C)

Max: +550°F (+287°C)

Pressure, max:

300 psi (20 bar)

Shaft speed:

To 2350 fpm (12 m/s)

pH range:

0–14

See reverse for ordering information.

ORDERING INFORMATION - PURE-PAC II

Specify Thomson style, size and quantity (lbs) required.

Size	1/8"	3/16"	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
Approx. (ft/lb)	72	31.5	19.4	12.5	9	5.1	3.3	2.3	1.7	1.2

Also available in metric sizes, die formed pre-packaged sets, and specialty cut lengths.
Contact A.R. Thomson Group for any special requirements.

SHAFT SPEED CONVERSION CALCULATIONS

Feet per minute (fpm)	Meter per second (m/s)
Shaft / sleeve diameter (in) x RPM x 0.262 = fpm	Shaft / sleeve diameter (in) x RPM x 0.0013299 = m/s
Shaft / sleeve diameter (mm) x RPM x 0.0103 = fpm	Shaft / sleeve diameter (mm) x RPM x 0.0000524 = m/s

AUTHORIZED DISTRIBUTOR

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.



Locations across Canada to serve you. For your nearest branch, please visit www.arthomson.com

Copyright © A.R. Thomson Group - All rights reserved. v.1.5