


Thomson THERMAPAC® 9100

Carbon Fiber / Nitrile Binder



FEATURES / BENEFITS

- High temperature capability, steam and chemical resistance.
- Flexible and easy to cut compared with typical carbon-based sheet.
- Reduces maintenance - maintains effective seal during pressure and thermal cycling (superior torque retention).

TYPICAL APPLICATIONS

- General service sheet packing material for demanding applications in Chemical, Pulp and Paper, Petroleum, Power Generation, and high temperature service in all industries.
- Saturated steam to 150 lbs, water, oils, gasoline, aliphatic hydrocarbons and most refrigerants.

“M & Y” FACTORS

Thickness		“m”	“y”
in	mm	(no units)	psi
1/16	1.6	3.7	3515
1/8	3.2	3.0	4014

SPECIFICATIONS

Construction: Carbon Fiber / Nitrile Binder

Temperatures:

Minimum: -100°F (-73°C)

Intermittent: +900°F (+482°C)

Continuous: +650°F (+343°C)

For steam applications above 150 lbs saturated contact A.R. Thomson Group.

Tensile Strength: 1800 psi

Pressure, max: 2000 psi

pH Range: 3–11

Color: Black with Black branding.

See reverse for more technical data.

*Maximum operating limits are conservative. Please contact an A.R. Thomson Group representative for higher pressures.

TECHNICAL DATA - THERMAPAC® 9100

Physical Properties		
TEST METHOD	TYPICAL PHYSICAL PROPERTIES	
ASTM F36	Compressibility: range, %	8–16
ASTM F36	Recovery: %	50
ASTM F38	Creep relaxation: 1/32" Thick, %	18
ASTM F152	Tensile across grain: psi (N/mm ²)	1800 (12)
ASTM F1315	Density: lbs/ft ³ (grams/cm ³)	100 (1.68)
ASTM D149	Dielectric breakdown: kv/mm	0.04
ASTM F586	Design Factors:	1/16" 1/8"
	"m" factor	3.7 3.0
	"y" factor, psi	3515 4014
ROTT	Gasket constants: 1/16"	Gb=1591 a=0.239 Gs=9.3
ASTM F104	Line call out:	F712120-B3E22M5

Immersion Properties* - ASTM F146 Fluid Resistance After Five Hours

	ASTM IRM #903 300°F (150°C)	ASTM FUEL B 70–85°F (20–30°C)
Thickness increase: %	0–10	0–10
Weight increase: %	10	12

Sealing Characteristics

	DIN 3535 NITROGEN
Leakage: ml/min	0.5

NOTES

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/16" (1.5 mm) sheet thickness unless otherwise mentioned.

*Values do not constitute specification Limits

² Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult A.R. Thomson Group. Minimum temperature rating is conservative.

³ Minimum recommended assembly stress=4800 psi. Preferred assembly stress=6000–10000 psi. Gasket thickness of 1/16" strongly preferred. Retorque the bolts/studs prior to pressurizing the assembly. For saturated steam above 150 psig or superheated steam, consult A.R. Thomson Group.

AUTHORIZED DISTRIBUTOR

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.



Locations across Canada to serve you. For your nearest branch, please visit www.arthomson.com

Copyright © A.R. Thomson Group - All rights reserved. v1.1