

Thomson

OPTI-LOAD® T-SHIELD



Peroxide cured EPDM rubber gasket with PTFE envelope to shield the gasket from contact with the process media.

FEATURES / BENEFITS

- Raised sealing rings reduce the seating area of the gasket, lowering the required load to achieve a seal.
- Sealing rings also help maintain the seal during thermal and pressure cycling.
- PTFE envelope is inert to virtually all chemical except for fluorine gases and molten alkali metals.
- Base gasket is Peroxide-cured EPDM which has superior chemical and heat resistance vs. standard EPDM for further reassurance.
- Identification tab on the outside diameter of the gasket allows operator to verify material and size while in service.

TYPICAL APPLICATIONS

- Non-metallic flanges and flanges that have limited seating stress available.
- Nearly all chemicals 0–14 pH.

SPECIFICATIONS

Construction:
Peroxide Cured EPDM
Rubber/Blue PTFE

Max Pressure:
150 psi (10 bar)

Colour:
Black/Blue

* See reverse for recommended bolt torque values.

Temperatures:
Minimum: -40°F (-40°C)
Intermittent: +300°F (+149°C)

TECHNICAL DATA - OPTI-LOAD® T-SHIELD

Bolt Torque Values for Thomson Opti-Load® Gaskets on ASME B16.5 Flat Face Flanges					
NPS (IN)	NO. OF BOLTS	SIZE OF BOLTS (IN)	MIN. SUGGESTED TORQUE (FT. LBS.)	PREFERRED TORQUE RANGE (FT. LBS.)	
				MIN	MAX
0.5	4	0.50	5	9	19
0.75	4	0.50	6	12	23
1	4	0.50	7	14	28
1.25	4	0.50	8	16	32
1.5	4	0.50	10	19	37
2	4	0.63	17	33	66
2.5	4	0.63	23	45	90
3	4	0.63	25	49	97
3.5	8	0.63	15	30	60
4	8	0.63	17	33	66
5	8	0.75	21	41	82
6	8	0.75	23	46	92
8	8	0.75	33	66	132
10	12	0.88	32	64	128
12	12	0.88	47	93	186
14	12	1.00	67	134	268
16	16	1.00	60	120	241
18	16	1.13	66	132	264
20	20	1.13	62	124	249
24	20	1.25	87	173	347

NOTES

This is a general guide and should not be the sole means of selecting or rejecting this material. Consult A.R. Thomson Group Inc. when approaching maximum pressure or temperature.

AUTHORIZED DISTRIBUTOR

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group Inc. does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.

arthomson.com



Locations across Canada to serve you. For your nearest branch, please visit: www.arthomson.com
Copyright © A.R. Thomson Group Inc. - All rights reserved.