

Thomson

OPTI-LOAD[®] AFLAS[®]



TYPICAL APPLICATIONS

- Non-metallic flanges and flanges that have limited seating stress available.
- Most chemical service (acid and caustic) where steam and hot water may be present.
- Chlor-Alkali applications such as Sodium Hypochlorite, and caustic soda.

OPTI-LOAD[®] AFLAS[®] gasket is a low load to seal gasket that is an extremely versatile elastomer with exceptional chemical and temperature capabilities. Especially suited for Chlor-Alkali plants.

FEATURES / BENEFITS

- Raised sealing rings reduce the seating area of the gasket, lowering the required load to achieve a seal.
- Sealing rings also help maintain the seal during thermal and pressure cycling.
- Excellent resistance to Steam and hot water.
- Excellent resistance to caustics and acids.
- Good resistance to most Hydrocarbons.
- Superior Dielectric strength.
- High Temperature capability compared to standard elastomers.
- Identification tab on the outside diameter of the gasket allows operator to verify material and size while in service.

SPECIFICATIONS

Construction:
AFLAS[®] Elastomer

Colour:
Black

Temperatures:
Minimum: -9°F (-16°C)
Intermittent: 400°F (203°C)

Durometer: 70
Shore A +/- 5%

Max Pressure:
150 psi (10 bar)

* See reverse for recommended bolt torque values and other technical data.

AFLAS[®] is a registered trademark of AGC Inc. Glass Company.

TECHNICAL DATA - OPTI-LOAD® AFLAS®

Physical Properties

TEST METHOD	TYPICAL PHYSICAL PROPERTIES	
ASTM D412	Elongation: %	271
ASTM D395B	Compression set before 22 hrs @ 175°C: %	11

Bolt Torque Values for Thomson OPTI-LOAD® Gaskets on ASME B16.5 Flat Face Flanges

NPS (IN)	NO. OF BOLTS	SIZE OF BOLTS (IN)	MIN. SUGGESTED TORQUE (FT. LBS.)	PREFERRED TORQUE RANGE (FT. LBS.)	
				MIN	MAX
0.5	4	0.50	5	9	19
0.75	4	0.50	6	12	23
1	4	0.50	7	14	28
1.25	4	0.50	8	16	32
1.5	4	0.50	10	19	37
2	4	0.63	17	33	66
2.5	4	0.63	23	45	90
3	4	0.63	25	49	97
3.5	8	0.63	15	30	60
4	8	0.63	17	33	66
5	8	0.75	21	41	82
6	8	0.75	23	46	92
8	8	0.75	33	66	132
10	12	0.88	32	64	128
12	12	0.88	47	93	186
14	12	1.00	67	134	268
16	16	1.00	60	120	241
18	16	1.13	66	132	264
20	20	1.13	62	124	249
24	20	1.25	87	173	347

AUTHORIZED DISTRIBUTOR

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group Inc. does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.

arthomson.com



Locations across Canada to serve you. For your nearest branch, please visit: www.arthomson.com

Copyright © A.R. Thomson Group Inc. - All rights reserved.